



Class:
EN ISO 20345:2011
S3 SRC
Sizes: 38-48
Instep: 12
Weight(±10%): 535 gr. (*)

TECHNICAL SHEET ART. JUNKERS

Description Low shoe in black Safety-Nabuk with padded storm-cuff, 100% polyester lining, Non-Metallic HRP Insole , ATOMIC Insole, double density polyurethane sole , bending resistant , abrasion resistant , oil resistant , slip resistant , ESD.

Plus Midsole compound particularly studied to get a soft PU density for a higher comfort

Suggested sectors of usage Building/Construction, Utilities, Mechanical Industry, Farming/Zootechnics , Naval Industry, Professional / Craftsman.

Care and Maintenance clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source.



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
Toe Cap: Non-Metallic TOP COMPOSITE toe cap, impact resistant 200 J	5.3.2.3 5.3.2.4	Impact resistance Compression resistance	mm mm	14,5 14,5	≥ 14 ≥ 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100 without holes	≥ 1.100
ESD footwear: dissipation capacity of the electrostatic charge	EN ISO 61340 5-1:2016	Resistance to floor (footwear/floor resistance) Transverse resistance of the sole Chargeability	Ohm Ohm V	4,67 x 10 ⁷ 3,20 x 10 ⁷ < 78 V	< 1,00 x 10 ⁸ Ω ≤ 1,00 x 10 ⁸ Ω < 100 V
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	24,0	≥ 20
Upper: Black Safety-Nabuk	5.4.6 5.4.3	Water vapour permeability Coefficient of permeability Tearing Strength Water absorption Water penetration	mg/cm ² h mg/cm ² N % g	5,4 49,1 65 19 0	≥ 0,8 ≥ 15 ≥ 60 ≤ 30 ≤ 0,2
Vamp Lining: honeycomb finished polyester, breathable, abrasion resistant, black colour	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (wet)	mg/cm ² h mg/cm ² N cycles cycles	6,8 54,4 25 no rupture no rupture	≥ 2 ≥ 20 ≥ 15 25.600 12.800
Quarter Lining: honeycomb finished polyester, breathable, abrasion resistant, light blue colour	5.5.3 5.5.1 5.5.2	Water vapour permeability Coefficient of permeability Tearing Strength Abrasion resistance (dry) Abrasion resistance (wet)	mg/cm ² h mg/cm ² N cycles cycles	6,5 54,3 27 no rupture no rupture	≥ 2 ≥ 20 ≥ 15 51.200 25.600
Insole lining: textile anti perforation midsole HRP insole	5.7.3	Water Absorption Ability to release water	mg/cm ²	76 99%	≥ 70 ≥ 80%
Sole: double density polyurethane , bending resistant, abrasion resistant, oil resistant, slip resistant, ESD	5.8.2 5.8.3 5.8.4 5.8.5 6.4.2 5.11	Tearing Strength Abrasion resistance Bending resistance Hydrolysis Hydrocarbons resistance (volume increase) Slip resistance on ceramic floor with water and detergent Slip resistance on steel floor with glycerine	kN/m mm ³ mm mm % flat inclined flat inclined	8,3 140 1,5 2,0 1,0% 0,45 0,30 0,25 0,21	≥ 8 ≤ 150 ≤ 4 ≤ 6 ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

Azocouleurants free : no presence of dangerous substances by Annex VII to regulation no. 1907/2006/CE and subsequent amendments and additions

(*) = Indicative weight that refers to ½ pair in size 42